

**AQUATOP 2600-12****Paint for frames**

PAINT TYPE AQUATOP 2600-12 is a water-borne acrylic-based top coat that is quick-drying and weather-resistant.

USAGE Door and window frames in horizontal lines. Before using the product, the manufacturer should be contacted to check the suitability of the product for the object in question.

TECHNICAL DATA

Solids 35 % by volume

Total mass of solids abt. 610 g/l

Volatile organic compound (VOC) abt. 28 g/l

Theoretical spreading rate 6.6 m²/l (wet film 150 µm, dry film 52 µm)

Drying time, +23°C, relative humidity 50% (120 µm wet film on glass plate)

- dust free after 25 min
- touch dry after 30 minutes

The drying times given are indicative because the product is intended for use on wooden substrates.

Overcoatable after about 1 h

Thinner, clean up Water

Finish Semi-matt

DIRECTION FOR USE**Surface preparation**

The surface must be clean and dry.
The moisture content of the wood is to be below 20%.

It is recommended that the wood is treated with an efficient wood preservative that protects it against rot, blue stain fungi and mildew.

Application conditions

The temperature of the air, the surface and the paint shall be above +15°C and the relative humidity of the air below 80% during the time of application and drying. The best result is achieved when the temperature of the air is +23 - +30°C, the relative humidity of the air 50 - 70% and the ventilation is good.

Application

Before use stir the paint thoroughly.

Apply by spray no more than 150 µm wet film in one coat. Minimum coating amount is 2 x 150 µm wet film. Also suitable for electrostatic spraying.

STORAGE

Must not freeze. The best storage temperature is between +10 - +25°C.

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.
